

## SEMICONDUCTOR VAPOR GROWTH METHOD

## SEMICONDUCTOR VAPOR GROWTH METHOD

Patent Number: JP1290221  
Publication date: 1989-11-22  
Inventor(s): OTSUKA NOBUYUKI; others: 02  
Applicant(s): FUJITSU LTD.  
Requested Patent: JP1290221  
Application Number: JP19880120872 19880518  
Priority Number(s):  
IPC Classification: H01L21/205  
EC Classification:  
EC Classification:  
Equivalents:

### Abstract

**PURPOSE:** To execute epitaxy of an atomic layer of a compound semiconductor at a low temperature by a method wherein an alkyl compound is supplied to the crystal surface of a substrate, heated hydrogen is supplied to the surface of the substrate and a raw material gas of another element constituting the compound semiconductor is supplied to the surface of the substrate.

**CONSTITUTION:** In a vapor growth epitaxial growth method of a compound semiconductor, e.g., a typical III to V compound, an alkyl metal as a raw material of a group III element is supplied to the crystal surface of a substrate 2; in a state that this alkyl metal has been adsorbed to the surface of the substrate 2, heated hydrogen is supplied and the alkyl metal in an adsorbed state is decomposed; a group III element layer is deposited; a raw material gas of a group V element is supplied. These raw material gases are introduced alternately into a reaction tube 1 by an operation of changeover valves 5, 5'. Although a temperature of heated hydrogen gas used for this treatment depends on an apparatus and a treatment condition, a substrate temperature + (300 to 800 deg.C) is suitable. By this setup, even when the substrate temperature is lowered, a self-layer limiting effect can be obtained surely, while epitaxy of an atomic layer can be executed easily.